



SPUNLACED POLYESTER
PERMATAPE™
WATERPROOFING
REINFORCING ONE-PLY SEAM TAPE

PRODUCT DATA	
2" x 100'	#9502-1
4" x 100'	#9504-1
8" x 100'	#9508-1
03/22/05	
<i>superseding: 01/01/97</i>	

PRODUCT DESCRIPTION:

PERMATAPE™ is a lightweight high strength material for waterproofing and reinforcing, when used in conjunction with an elastomeric coating or primer saturant. The fabric is 100% polyester continuous filament, spunlaced structures, entangled hydraulically to form a strong, yet conforming membrane. PERMATAPE™ offers the user a new material with extraordinary physical and chemical properties, replacing fiberglass and organic felts, and is non-irritating to the skin. It maintains its physical properties when wet and is dimensionally stable during humidity changes. PERMATAPE™ has excellent chemical resistance and is also resistant to rot and mildew. It is used to strengthen and reinforce seams and potential problem areas.

The design of the fabric tape eliminates air pockets and allows the elastomeric coating or primer saturant to flow through and absorb, forming an impenetrable barrier to water and most other liquids. The excellent conformability of the fabric makes PERMATAPE™ perfect for irregular applications on vertical or horizontal surfaces.

PERMATAPE™ USES:

PERMATAPE™ can be used on any substrate with which the saturant is compatible. Refer to the Product Uses of the data sheet for the specific coating or primer saturant that will be used.

SURFACE PREPARATION:

Refer to the Surface Preparation of the data sheet for the specific coating or primer saturant that will be used.

RECOMMENDED SATURANTS:

Include, but are not limited to: **ROOF-PRIME™**, **PERMABOND™**, **METAL-PRIME**, or **ULTRA PRIME™**, using a minimum 1.5 gallons of saturant per 100 square feet of tape (*Amount of saturant may vary due to porosity and condition of surface*):

2" x 100' = .25 Gallons 4" x 100' = .5 Gallons 8" x 100' = 1 Gallon

APPLICATION PROCEDURE:

Apply a liberal amount of saturant to the surface area to be taped about 2 to 4 inches wider than the tape so that the total area underneath the tape is saturated. Tape must be laid or rolled into the WET saturant. Do not coat too big an area since the saturant might dry before the tape can be applied. Form the tape into the wet saturant conforming it to the contour of the surface thereby eliminating any air pockets, wrinkles or bunching up of the tape. A high density, short nap roller can be used on even surfaces to flatten and smooth out the tape. Let this procedure dry for approximately 1 to 2 hours depending on temperature and humidity. Apply a second light coat of saturant over the tape thus sandwiching the tape between the two coats of saturant. Let this final coat of saturant dry for approximately 1 to 2 hours before applying a primer or coating.

Custom Widths and Lengths are available, but are subject to minimum order quantities, Inquire for Details.

PHYSICAL PROPERTIES

WEIGHT per 100 SQUARE FEET:	1.1 pounds	ASTM D3776
OUNCES per SQUARE YARD:	1.6 ounces	ASTM D3776
DRY TENSILE – MD (length):	25 pounds	ASTM D1777
DRY TENSILE – CD (width):	18 pounds	ASTM D1777
ELONGATION – MD (length):	45%	ASTM D1682
ELONGATION – CD (width):	100%	ASTM D1682
MULLEN BURST:	35 p.s.i.	ASTM D3786

TECHNICAL SPECIFICATIONS:

COLOR:	White	ROLL SIZE(s) (inches):	2" or 4" or 8" x 100 Feet
FABRIC:	100% Polyester	BULK:	22.0 mils (80% absorption)
WEIGHT per ROLL:	2": 0.25 lbs. +/- 10%	PACKAGING:	2": Case of 24 Rolls
	4": 0.5 lbs. +/- 10%		4": Case of 12 Rolls
	8": 1 lb. +/- 10%		8": Case of 12 Rolls

Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.

In Any Event Nationwide Chemical Coating Manufacturers, Inc. will not be liable or responsible for any past, present or future leaks or any resulting consequential or incidental damages.



MATERIALS HEALTH, SAFETY AND
ENVIRONMENTAL DATA SHEET

MSDS#:
9500

This is to advise
the user that
PERMATAPE™
is exempt from the
OSHA
Hazard Communications Standard
since it contains less than
1 percent
of any hazardous ingredient.